

ANALYSE CERTIFICAAT

CERTIFICAAT NO. 1020811.001G

KLANT

KLANT REF.

PPG Coatings Deutschland GmbH
An der Halde 1
44805 Bochum
Deutschland

MONSTER DETAILS

DATUM ONTVANGEN 11-Feb-13

Sigmarest Immun Mat

METHODE: (Bepaling Van De Antibacteriële Activiteit Met Behulp Van De Test Gebaseerd Op MOD ISO 22196:2011)

DATUM GEANALYSEERD 13-Feb-13

DATUM GERAPPORTEERD 27-May-13

RESULTATEN (IN CFU CM -2)

SAMPLE		CONTACT TIJD		BACTERIËLE VERMINDERING	
		0 UUR	24 UUR	Log	%
Polypropylene Control (IMSL)	<i>E coli</i>	1.8E+04	1.7E+05	-	-
Sigmarest Immun Mat	<i>E coli</i>	1.8E+04	≤ 1.0	≥ 4.2	≥ 99.99
Polypropylene Control (IMSL)	<i>S aureus</i>	1.6E+04	8.6E+03	0.3	47.25
Sigmarest Immun Mat	<i>S aureus</i>	1.6E+04	≤ 1.0	≥ 4.2	≥ 99.99
Polypropylene Control (IMSL)	MRSA	1.6E+04	4.3E+03	0.6	72.61
Sigmarest Immun Mat	MRSA	1.6E+04	≤ 1.0	≥ 4.2	≥ 99.99
Polypropylene Control (IMSL)	<i>Ps aeruginosa</i>	1.7E+04	2.6E+05	-	-
Sigmarest Immun Mat	<i>Ps aeruginosa</i>	1.7E+04	≤ 1.0	≥ 4.2	≥ 99.99

Bovenstaande gegevens tonen het verschil in de populatie na contact met het oppervlak van de genoemde monsters gedurende 24 uur bij 35 ° C onder een relatieve luchtvochtigheid van > 95% ten opzichte van de controlepopulatie.

INDUSTRIAL MICROBIOLOGICAL SERVICE LTD
PALE LANE
HARTLEY WINTNEY
HANTS
RG27 8DH
UK

PETER D ASKEW
MANAGING DIRECTOR



ANALYSE CERTIFICAAT

CERTIFICAAT NO. 1020811.001H

KLANT

KLANT REF.

PPG Coatings Deutschland GmbH
An der Halde 1
44805 Bochum
Deutschland

MONSTER DETAILS

DATUM ONTVANGEN 11-Feb-13

Sigmaresist Immun Mat

METHODE: (Bepaling Van De Antibacteriële Activiteit Met Behulp Van De Test Gebaseerd Op MOD ISO 22196:2011)

DATUM GEANALYSEERD 13-Feb-13

DATUM GERAPPORTEERD 27-May-13

RESULTATEN (IN CFU CM -2)

SAMPLE		CONTACT TIJD		BACTERIËLE VERMINDERING	
		0 UUR	24 UUR	Log	%
Polypropylene Control (IMSL)	<i>E hirae</i>	1.9E+04	1.9E+04	-	-
Sigmaresist Immun Mat	<i>E hirae</i>	1.9E+04	≤ 1.0	≥ 4.3	≥ 99.99
Polypropylene Control (IMSL)	<i>A baumannii</i>	2.5E+04	9.7E+05	-	-
Sigmaresist Immun Mat	<i>A baumannii</i>	2.5E+04	≤ 1.0	≥ 4.4	≥ 99.99
Polypropylene Control (IMSL)	<i>S pneumoniae</i>	2.2E+04	1.1E+01	3.2	99.95
Sigmaresist Immun Mat	<i>S pneumoniae</i>	2.2E+04	≤ 1.0	≥ 4.3	≥ 99.99
Polypropylene Control (IMSL)	<i>K pneumoniae (CPE)</i>	1.8E+04	2.8E+05	-	-
Sigmaresist Immun Mat	<i>K pneumoniae (CPE)</i>	1.8E+04	≤ 1.0	≥ 4.3	≥ 99.99

Bovenstaande gegevens tonen het verschil in de populatie na contact met het oppervlak van de genoemde monsters gedurende 24 uur bij 35 ° C onder een relatieve luchtvochtigheid van > 95% ten opzichte van de controlepopulatie.

INDUSTRIAL MICROBIOLOGICAL SERVICE LTD
PALE LANE
HARTLEY WINTNEY
HANTS
RG27 8DH
UK

PETER D ASKEW
MANAGING DIRECTOR



IMSL

INDUSTRIAL MICROBIOLOGICAL SERVICES LTD

STUDY REPORT: Determination of the Antibacterial Activity of Paint Samples against *Escherichia coli*, *Staphylococcus aureus*, MRSA, *Pseudomonas aeruginosa*, *Enterococcus hirae*, *Acinetobacter baumannii*, *Streptococcus pneumoniae* and Carbapenemase Producing *Klebsiella pneumoniae* using Modified ISO 22196: 2011.

CLIENT: PPG Coatings Deutschland GmbH
An der Halde 1
44805 Bochum
Deutschland

REPORT NO: IMSL 2012/11/012.1A-2

DATED: 27th May 2013

Study: Determination of the Antibacterial Activity of Paint Samples against *Escherichia coli*, *Staphylococcus aureus*, MRSA, *Pseudomonas aeruginosa*, *Enterococcus hirae*, *Acinetobacter baumannii*, *Streptococcus pneumoniae* and Carbapenemase Producing *Klebsiella pneumoniae* using Modified ISO 22196: 2011.

Number: IMSL 2012/11/012.1A-2

Client: PPG Coatings Deutschland GmbH

The above study was conducted in the laboratories of Industrial Microbiological Services Ltd at Pale Lane Hartley Wintney, Hants, RG27 8DH, UK. This report represents a true and accurate account of the results obtained.

Start Date 13th February 2013

Report Issued 08th May 2013

Report Reissued 27th May 2013 (Name Change)

Supervisor Kyle Allison
Senior Microbiologist



Operator Richard Webb
Microbiologist



Contents

1	Introduction	1
2	Test Materials	1
3	Methods	1
3.1	Determination Antibacterial Activity	1
4	Results / Discussion	3
5	Raw Data	10
6	References	10
7	Exclusion of Liability	11

1 Introduction

This report summarises a study performed to assess the antibacterial performance of Paint Formulations against *Escherichia coli*, *Staphylococcus aureus*, MRSA, *Pseudomonas aeruginosa*, *Enterococcus hirae*, *Acinetobacter baumannii*, *Streptococcus pneumoniae* and Carbapenemase Producing *Klebsiella pneumoniae* using the method described in ISO 22196: 2011.

2 Test Materials

Leneta scrub resistance test panels coated with paint formulations prepared with an antimicrobial agent were supplied by PPG Coatings Deutschland GmbH. All samples were held in the dark at 20°C prior to testing. An inert sample of Polypropylene was supplied by IMSL to act as a reference material.

3 Methods


Antibacterial activity was determined using the method described in ISO 22196: 2011 (Ref 1).

3.1 Determination of Antibacterial Activity

An aliquot (225µl) of a log phase cell suspension of either *Escherichia coli*, *Staphylococcus aureus*, MRSA, *Pseudomonas aeruginosa*, *Enterococcus hirae*, *Acinetobacter baumannii*, *Streptococcus pneumoniae* or Carbapenemase Producing *Klebsiella pneumoniae* prepared using the method described in ISO 22196 : 2011 were held in intimate contact with multiple replicates of the test surfaces supplied using a 30 x 30 mm polyethylene film (cut from a sterile Stomacher bag) for 12 and 24 hours at 35°C, except in the case of *Klebsiella pneumoniae* which was assessed after 6, 12, 18 and 24 hours. The size of the surviving population was determined using the method described in ISO 22196 : 2011. The viable cells in the suspension were enumerated by spiral dilution on to Trypcase Soya Agar and by the pour plate method described in ISO 22196 These plates were then incubated at 35°C for 24 hours and then counted. An additional 3 replicate unfortified surfaces were also inoculated in the manner described above but were then analysed immediately for the size of microbial population present to provide 0-time control data. The method is described schematically in Figure 1 below.

All data were converted to colony forming units (CFU) cm² and then transformed (Log₁₀) to provide a data set that conformed to a gaussian distribution. Potential outliers were tested using Dixon's *Q*-test (P = 0.05).

Figure 1: ISO 22196 : 2011 - Schematic Representation



4 Results / Discussion

The results are shown in Tables 1- 8 and Figures 2 - 4.

Table 1: Activity Against *E coli*
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time		
	0 hours	12 hours	24 hours
Polypropylene Control (IMSL)	1.8 x 10 ⁴	1.4 x 10 ⁴	1.7 x 10 ⁵
Sigmarest Immun Mat	1.8 x 10 ⁴	≤ 1.0	≤ 1.0

‡ The theoretical limit of detection is 1 CFU cm⁻²

It can be seen from the data above that the population of *Escherichia coli* exposed to the unfortified IMSL polypropylene control remained relatively constant during the initial 12 hour contact interval and then increased by 1 order of magnitude after 24 hours. This is considered a normal response for this organism on an inert surface under the conditions imposed by ISO 22196. A reduction of ≥ 4.2 orders of magnitude was observed in the populations held in contact with the samples of Sigmarest Immun Mat after 12 hours.

Table 2: Activity Against *S aureus*
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time		
	0 hours	12 hours	24 hours
Polypropylene Control (IMSL)	1.6 x 10 ⁴	1.4 x 10 ⁴	8.6 x 10 ³
Sigmarest Immun Mat	1.6 x 10 ⁴	≤ 1.0	≤ 1.0

It can be seen from the data above that the population of *Staphylococcus aureus* exposed to the unfortified IMSL polypropylene control remained relatively constant during the initial 12 hour contact interval and then decreased by 0.3 orders of magnitude during the second 12 hour interval. This is again considered a normal response for this organism on an inert surface under the conditions imposed by ISO 22196. A reduction of ≥ 4.2 orders of magnitude was observed in the populations of *Staphylococcus aureus* held in contact with the samples of Sigmarest Immun Mat after 12 hours.

Table 3: Activity Against MRSA
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time		
	0 hours	12 hours	24 hours
Polypropylene Control (IMSL)	1.6 x 10 ⁴	1.0 x 10 ⁴	4.3 x 10 ³
Sigmarest Immun Mat	1.6 x 10 ⁴	≤ 1.0	≤ 1.0

The data in Table 3 above shows that the population of Methicillin Resistant *Staphylococcus aureus* exposed to the unfortified IMSL polypropylene control declined by 0.2 orders of magnitude during the initial 12 hour contact interval and by a further 0.4 orders of magnitude over the remaining 12 hours. This is again considered a normal response for this organism on an inert surface under the conditions imposed by ISO 22196. A reduction of ≥ 4.2 orders of magnitude was observed in the populations of MRSA held in contact with the samples of Sigmarest Immun Mat after 12 hours.

Table 4: Activity Against *Ps aeruginosa*
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time		
	0 hours	12 hours	24 hours
Polypropylene Control (IMSL)	1.7 x 10 ⁴	5.6 x 10 ³	2.6 x 10 ⁵
Sigmarest Immun Mat	1.7 x 10 ⁴	≤ 1.0	≤ 1.0

Table 4 shows that the population of *Pseudomonas aeruginosa* exposed to the unfortified IMSL polypropylene control declined by 0.5 orders of magnitude during the initial 12 hour contact interval and then increased by 1.7 orders of magnitude over the remaining 12 hours. This could be attributed to the surviving population receiving a nutrient source from the dead bacterial population allowing it to recover and grow. In contrast, the populations of *Pseudomonas aeruginosa* exposed to the surfaces of Sigmarest Immun Mat declined by ≥ 4.2 orders to below the limit of detection after 12 hours.

Table 5: Activity Against *E hirae*
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time		
	0 hours	12 hours	24 hours
Polypropylene Control (IMSL)	1.9 x 10 ⁴	1.3 x 10 ⁴	1.9 x 10 ⁴
Sigmaresist Immun Mat	1.9 x 10 ⁴	3.7 x 10 ⁰	≤ 1.0

The data in Table 5 above shows that the population of *Enterococcus hirae* exposed to the unfortified IMSL polypropylene control declined by 0.2 orders of magnitude during the initial 12 hour contact interval and recovered back to its original level over the remaining 12 hours. In contrast, the population of the population of *Enterococcus hirae* exposed to Sigmaresist Immun Mat declined by 3.7 orders of magnitude after 12 hours and to below the limit of detection after 24 hours.

Table 6: Activity Against *A baumannii*
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time		
	0 hours	12 hours	24 hours
Polypropylene Control (IMSL)	2.5 x 10 ⁴	1.8 x 10 ⁵	9.7 x 10 ⁵
Sigmaresist Immun Mat	2.5 x 10 ⁴	≤ 1.0	≤ 1.0

The data in Table 6 shows that the population of *Acinetobacter baumannii* exposed to the unfortified IMSL polypropylene control increased after 12 and 24 hours by a total of 1.6 orders of magnitude. In contrast, the populations of *Acinetobacter baumannii* exposed to the surfaces of Sigmaresist Immun Mat declined by 4.4 orders to below the limit of detection after 12 hours.

Table 7: Activity Against *S pneumoniae*
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time		
	0 hours	12 hours	24 hours
Polypropylene Control (IMSL)	2.2 x 10 ⁴	1.1 x 10 ³	1.1 x 10 ¹
Sigmaresist Immun Mat	2.2 x 10 ⁴	≤ 1.0	≤ 1.0

It can be seen from the data above that the population of *Streptococcus pneumoniae* exposed to the polypropylene reference material declined by 1.8 orders of magnitude during the first 12 hours and then by a further 1.9 orders of magnitude during the second 12 hour interval. After 12 hours, the population of *Streptococcus pneumoniae* exposed to the samples of Sigmaresist Immun Mat declined by 4.3 orders of magnitude to below the limit of detection.


Table 8: Activity Against Carbapenemase Producing *K pneumoniae*
(Geometric Mean of Replicates as Colony Forming Units cm⁻²)

Sample	Contact Time				
	0 hours	6 hours	12 hours	18 hours	24 hours
Polypropylene Control (IMSL)	1.8 x 10 ⁴	1.3 x 10 ⁴	7.5 x 10 ⁴	5.7 x 10 ⁴	2.8 x 10 ⁵
Sigmaresist Immun Mat	1.8 x 10 ⁴	≤ 1.0	≤ 1.0	≤ 1.0	≤ 1.0

The data in Table 8 shows that the population of Carbapenemase Producing *Klebsiella pneumoniae* exposed to the unfortified IMSL polypropylene control gradually increased by up to 1.1 orders of magnitude after 24 hours. In contrast, a reduction of 4.4 orders of magnitude to below the limit of detection of *Klebsiella pneumoniae* was observed on the samples of Sigmaresist Immun Mat after 6 hours.


Figure 2: Results as $\text{Log}_{10} \text{CFU cm}^{-2}$

E coli




—○— Polypropylene —○— Sigmaresist Immun Mat

S aureus



—○— Polypropylene —○— Sigmaresist Immun Mat


MRSA




—○— Polypropylene —○— Sigmaresist Immun Mat

Figure 3: Results as $\text{Log}_{10} \text{CFU cm}^{-2}$

Ps aeruginosa



E hirae



A baumannii






Figure 4: Results as Log₁₀ CFU cm⁻²

S pneumoniae



Carbapenemase Producing *K pneumoniae*



5 Raw Data

The raw data for this study will be held in file IMSL 2012/11/012 in the Archive of IMSL at Pale Lane, Hartley Wintney, Hants, RG27 8DH, UK for 6 years from the date of this report unless other specific instructions are given.

6 References

- 1 ISO 22196:2011 - Measurement of antibacterial activity on plastics and other non-porous surfaces

7 Exclusion of Liability

The contents of this report are subject to the standard terms and conditions of IMSL as displayed on the reverse of the invoice. Specific attention is drawn to Section 10 restated below.

- (a) IMSL warrants that the results as stated in this Report are accurate in so far as they relate to the Samples as received in the laboratory of IMSL. Except in respect of death or personal injury caused by IMSL's negligence IMSL accepts no other liability or responsibility to any party whatsoever (whether caused by the negligence of IMSL, its employees, or agents or otherwise) arising out of or in connection with the provision of this Report. In particular, but without prejudice in the generality of the foregoing IMSL shall have no liability or responsibility whatsoever in respect of or in any way by reference to:-
- (i) the taking of the Samples (unless this is done by an agent of IMSL), the accuracy of the Samples or their suitability for the purpose(s) for which they were taken or applied, the designation, handling, storage or transport of the Samples prior to their delivery to the laboratory of IMSL or their condition upon such delivery
 - (ii) the interpretation of the Report and / or the application of the results as stated and / or the accuracy of any advices based thereon
 - (iii) any (or any alleged) lack of competence, negligence, failure or breach of duty on the part of any person engaged in or responsible for any of the activities or functions referred to above whether or not such agent is described as an agent of IMSL or otherwise. All such persons shall be deemed to be agents of the Customer and not to be agents or representatives in any capacity of IMSL
 - (iv) incorrect information or data supplied by the Customer relating to the Samples
 - (v) loss of or damage to the Samples when in the possession of IMSL
 - (vi) delay in provision of the Service or mis-delivery or non-delivery of any Report or Sample.
- (b) In the event of any claim arising against IMSL, IMSL expressly excludes liability for any consequential loss or damage or any loss of value, profit, business, revenue, goodwill, yields, production or anticipated saving which may arise in respect of or in any way by reference to any Report, analysis, advice or information given verbally by any person or contained in any Report, leaflet, book, pamphlet, brochure or any other document, whether prepared, published or issued by IMSL or otherwise.